

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>C08L 53/00</b>	<b>A1</b>	(11) International Publication Number: <b>WO 98/37144</b> (43) International Publication Date: 27 August 1998 (27.08.98)
<p>(21) International Application Number: PCT/EP98/00859</p> <p>(22) International Filing Date: 16 February 1998 (16.02.98)</p> <p>(30) Priority Data: 97200530.0 21 February 1997 (21.02.97) EP (34) Countries for which the regional or international application was filed: NL et al.</p> <p>(71) Applicant (for all designated States except US): MONTELL TECHNOLOGY COMPANY B.V. [NL/NL]; Hocksteen 66, NL-2132 MS Hoofddorp (NL).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): PELLEGATI, Giampaolo [IT/IT]; Via Ca Nove, 4, I-44032 Baure (IT). BRAGA, Vittorio [IT/IT]; Via G. Meli, 12, I-44100 Ferrara (IT). BONARI, Roberto [IT/IT]; Via Vittorio Veneto, 12, I-20023 Cerro Maggiore (IT).</p> <p>(74) Agent: ZANOLI, Enrico; Montell Italia S.p.A., Intellectual Property Patents and Trademarks, Via Pergolesi, 25, I-20124 Milano (IT).</p>		<p>(81) Designated States: AU, BR, CA, JP, KR, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p><b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: SOFT ELASTOMERIC THERMOPLASTIC POLYOLEFIN COMPOSITIONS</p> <p>(57) Abstract</p> <p>An elastomeric thermoplastic polyolefin composition comprising (I) an heterophasic olefin polymer composition comprising a crystalline propylene homopolymer of copolymer fraction and an elastomeric ethylene copolymer fraction and (II) an elastomeric polymer having a hardness equal to or less than 90 points selected from the group consisting of copolymers of ethylene, ethylene-methyl acrylate copolymers, saturated or unsaturated styrene blocs copolymers and unsaturated norbornene polymers.</p>		

present it is requested that manufactured articles used to coat internal parts of vehicles be opaque.

Moreover, although the cited compositions are soft, they do not meet the present requirements entirely, as to meet them it is necessary to produce soft compositions.

Finally, the above-mentioned prior art compositions have the drawback of showing a marked stickiness, badly affecting the aesthetic appearance.

To overcome the drawbacks of the known polymers and meet the said requirements, now a new composition has been found which has higher softness and less stickiness.

Besides, the manufactured articles produced with the composition of the present invention are opaque.

Another advantage given by the composition of the present invention concerns the good workability of the composition in a broad range of temperatures. One does not observe a meaningful variation of the proprieties of the compositions in such range, with particular reference to the surface reproducibility, i.e. a good and constant quality of the embossing or roughness, planarity of the moulded surface and absence of the stickiness even after ageing.

A further advantage of the composition of the present invention is that it has good softness even in the absence of the extender oil. As well known the extender oil can be released by the composition containing it as time passes and cause pollution and fogging. Moreover, articles obtained by the composition containing extender oils can become gloss and greasy because of the emergence of said oil.

Therefore, an object of the present invention is an elastomeric thermoplastic polyolefin composition comprising (percent by weight):

- (I) 40-97%, preferably 45-95%, of a heterophasic olefin polymer composition comprising:
  - (A) 5-50%, preferably 10-40 %, of a crystalline propylene homopolymer with isotactic index greater than 80%, preferably from 85 to 90%, or crystalline copolymer of propylene and ethylene or a  $\text{CH}_2=\text{CHR}$   $\alpha$ -olefin, wherein R is a  $\text{C}_2\text{-C}_8$  alkyl radical, or crystalline copolymer of propylene, ethylene and a  $\text{CH}_2=\text{CHR}$   $\alpha$ -olefin, wherein R is a  $\text{C}_2\text{-C}_8$  alkyl radical, or blend thereof; said copolymers containing more than 85% of propylene and having an isotactic index greater than 80%;
  - (B) 0-20%, preferably 0-15%, of a crystalline copolymer fraction of ethylene with propylene or with a  $\text{CH}_2=\text{CHR}$   $\alpha$ -olefin, wherein R is a  $\text{C}_2\text{-C}_8$  alkyl radical, or both propylene and said alpha-olefin, said fraction being insoluble in xylene at ambient temperature, i.e. 25°C; and
  - (C) 40-95%, preferably 50-75%, of an elastomeric copolymer fraction of ethylene with propylene or with a  $\text{CH}_2=\text{CHR}$   $\alpha$ -olefin, wherein R is a  $\text{C}_2\text{-C}_8$  alkyl radical, or both propylene and said alpha-olefin, and optionally with minor amounts of a diene, said copolymer fraction containing ethylene in an amount smaller than 40%, preferably from 20 to 38%, and being soluble in xylene at ambient temperature;

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

(II) 3-60%, preferably 5-55%, of an elastomeric polymer having a hardness (Shore A, ASTM D-2240) equal to or less than 90 points, preferably equal to or less than 88 points, more preferably equal to or less than 75 points, selected from the group consisting of:

- 1 copolymers of ethylene with a  $C_3$ - $C_{10}$   $\alpha$ -olefin containing at least 20 wt%, preferably from 20 to 70 wt%, of  $C_3$ - $C_{10}$   $\alpha$ -olefin ( $^{13}C$ -NMR analysis) and having a Mw/Mn ratio less than 4, preferably less than 3;
- 2 ethylene-methyl acrylate copolymers containing from 15 to 30 wt% of methyl acrylate units and having MFR from 1 to 10 g/10 min (ASTM D-1238);
- 3 saturated or unsaturated styrene block copolymers, linear or branched, containing at least one comonomer selected from butadiene, butylene, ethylene and isoprene; and
- 4 unsaturated norbornene polymers having a molecular weight over 3,000,000.

Examples of heterophasic olefin polymer composition (I) are described in published European patent application EP-A-0 472946 (Himont Inc.), the content of which is incorporated herein by reference.

As a way of example the total amount of ethylene in heterophasic olefin polymer composition (I) is 15 to 35% by weight. Besides, the intrinsic viscosity of fraction (C) generally is 1.5 to 4 dl/g.

Preferably the propylene content in copolymers of fraction (A) is 90 to 99% by weight. The isotactic index is determined as the insoluble fraction in xylene at 25°C (see note 1 below).

Preferably the amount of ethylene in fraction (B) is at least 75% by weight, more preferably at least 80% by weight, with respect to the total weight of (B). Preferably the copolymer is an essentially linear copolymer of ethylene with propylene, such as a linear low density polyethylene (LLDPE).

Examples of  $\text{CH}_2=\text{CHR}$   $\alpha$ -olefin, wherein R is a  $\text{C}_2\text{-C}_8$  alkyl radical, that can be present in heterophasic polymer composition (I) are 1-butene, 1-pentene, 4-methyl-1-pentene, 1-hexene and 1-octene.

When present, the diene units in fraction (C) of (I) are preferably in an amount from 1% to 10% by weight with respect to the total weight of (C). Examples of dienes are butadiene, 1,4-hexadiene, 1,5-hexadiene and ethylene-1-norbornene.

The above-mentioned heterophasic olefin polymer composition (I) can be prepared by melt blending fractions (A), (B) and (C) in the fluid state, that is at temperatures higher than their softening or melting point, or by sequential polymerization in two or more stages in the presence of a highly stereospecific Ziegler-Natta catalyst. In particular the catalyst system comprises (i) a solid catalyst component containing a titanium compound and an electron-donor compound both supported on a magnesium halide and (ii) an Al-trialkyl compound and an electron-donor compound.

Examples of sequential polymerization processes are described in published European patent application EP-A-0 472 946. When heterophasic olefin polymer composition (I) is prepared by sequential polymerization, fraction (B) is present in an amount greater than or equal to 1% by weight. When said fraction (B) is present, it is preferable that the (B)/(C) weight ratio be less than 0.4, in particular from 0.1 to 0.3. It is also

preferable that the weight percent of fraction (C), or of the sum of fractions (B) and (C), be from 50 to 90%, preferably from 65 to 80%, with respect to heterophasic olefin polymer composition (I).

Heterophasic olefin polymer composition (I) has preferably Melt Flow Rate (MFR) (according to ASTM D 1238, condition L) values generally comprised in the range from 0.1 to 100 g/10 min, preferably from 0.2 to 50 g/10 min. Heterophasic olefin polymer composition (I) having said values of MFR can be obtained directly during the polymerization process; otherwise heterophasic olefin polymer composition (I) can undergo a visbreaking process carried out in the presence of visbreaking agents, such as peroxides. The said visbreaking process is carried out according to well-known methods.

Preferably polymers 1 having the cited  $\overline{M}_w/\overline{M}_n$  ratio are obtained directly by the polymerization process, i.e. in the absence of chemical visbreaking, by peroxides for instance. Polymers 1 can be prepared with metallocene catalysts, for example.

Preferred examples of elastomeric polymers 1 are:

- (a) elastomeric copolymers of ethylene with 1-octene having from 20 wt% to 40 wt% of 1-octene ( $^{13}\text{C}$ -NMR analysis); preferably having density of less than 0.89 g/ml;
- (b) elastomeric thermoplastic copolymers of ethylene with 1-butene having from 20 wt% to 40 wt% of 1-butene ( $^{13}\text{C}$ -NMR analysis); preferably having density of less than 0.89 g/ml;

Preferred examples of elastomeric copolymers 2 are:

- (c) ethylene-methyl acrylate copolymers containing about 20-25 wt% of methyl acrylate units and having MFR from 1.5 to 6 g/10 min.

Preferred examples of elastomeric copolymers 3 are:

- (d) unsaturated linear block copolymers of styrene with isoprene or butadiene and saturated linear block copolymers of styrene with ethylene and butylene.

The copolymers of groups 1 to 3 are preferred. In particular copolymers (a) and (b) are more preferred, more particularly copolymers (a) are the most preferred.

A specific example of copolymers (a) is a copolymer containing 66 wt% of ethylene and 34 wt% of 1-octene ( $^{13}\text{C}$ -NMR analysis, see note 2 below), having a hardness of 75 Shore A points, a MFR of 10 g/10 min and a density of 0.87 g/ml according to method ASTM D 792.

Another specific example of copolymers (a) is a copolymer containing 75 wt% of ethylene and 25 wt% of 1-octene (IR analysis), having a hardness of 75 Shore A points and a density of 0.87 g/ml according to method ASTM D 792 and MFR of about 1 g/10 min.

A specific example of copolymers (b) is a copolymer containing 77.9 wt% of ethylene and 22.1 wt% of 1-butene ( $^{13}\text{C}$ -NMR analysis, see note 2 below), having a hardness of 85 Shore A points and a density of 0.87 g/ml according to method ASTM D 792.

A specific example of copolymers (c) is an ethylene-methyl acrylate copolymer containing 20 wt% of methyl acrylate, having a MFR of 1.5-2.5 g/10 min, a hardness of 89 Shore A points and a density of 0.945 g/ml according to method ASTM D 792.

Specific example of copolymers (d) are styrene-isoprene-styrene block copolymers (SIS), commercialised as Kraton D-1112, having a hardness of 34 Shore A points; styrene-ethylene-butylene-styrene block copolymers (SEBS), marketed as Kraton G-1652, having a hardness of 75 Shore A points; and



styrene-ethylene-butylene-styrene block copolymers (SEBS), marketed as Kraton G-1657, having a hardness of 65 Shore A points. They all are commercialised by Shell.

A specific example of polymer 4 is the one having a molecular weight over 3,000,000; it is marketed by Nippon Zeon Co. LTD with the trademark Norsorex N.

The compositions of the present invention can also contain various additives generally used in the polymeric thermoplastic compositions, such as stabilizers, anti-oxidizing agents, anti-corrosion agents, anti-UV agents, carbon black, pigments, plasticizers and so on. Furthermore, the compositions according to the present invention can contain additives, flame retardants and fillers, such as mineral fillers, capable of giving particular properties to the articles for the manufacture of which the compositions are made.

The compositions of the present invention can be prepared by blending the components in an apparatus equipped with mixing elements, such as an internal mixer or extruder. For example one can use a Banbury mixer or single-screw Buss extruder or twin-screw Maris or Werner type extruder.

The composition of the present invention can be prepared in one or more stage(s). The order of mixing of the components is not relevant. The visbreaking of heterophasic olefin polymer composition (I) through visbreaking agents can be carried out in the presence of elastomeric polymer (II), and optionally other additives, as well as before adding elastomeric polymer (II) or after the addition thereof.

The compositions of the invention are generally obtained in form of pellets. These can be transformed into shaped manufactured articles by known injection, co-injection

moulding, sequential injection moulding and blow moulding processes and transformed into laminates, which include films and laminates, by extrusion.

Generally speaking, preferably, the compositions of the present invention suitable for injection moulding processes have values of MFR ranging about from 2 to 100 g/10 min, preferably from 2 to 50 g/10 min. The compositions having lower values of MFR, such as from 0.1 to 2 g/10 min, preferably from 0.2 to 2 g/10 min, are suitable for extrusion processes.

The following examples are given to illustrate, but not limit the present invention.

The method used to obtain the property data reported in the examples and description are identified below.

<u>Property</u>	<u>Method</u>
- Melt Flow Rate	ASTM D-1238, condition L
- Intrinsic viscosity	Determined in tetrahydro-naphthalene at 135°C
- Xylene soluble fraction	(see note 1 below)
- Determination of C content	<sup>13</sup> C-NMR analysis (see note 2 below)
- Hardness (Shore D)	ASTM D-2240
- Hardness (Shore A)	ASTM D-2240
- Gloss	(see note 3 below)
- Stickiness	(see note 4 below)
- Blooming	(see note 5 below)
- Coefficient of friction (COF)	ASTM D-1894, condition C (see note 6 below)
- Roughness	DIN 4768 (see note 7 below)
- Planarity	ASTM D-4771 (see note 8 below)

- |                            |   |
|----------------------------|---|
| - Elongation at break      | ASTM D-638  |
| - Tensile at break         | ASTM D-638  |
| - Tension set 100% at 23°C | ASTM D 412, cut according to<br>method ASTM D 638 |

Note 1

Determination of the percent of xylene soluble fraction: a solution of the sample in xylene at a concentration of 1% by weight is prepared and kept at 135°C for one hour while stirring. The solution is allowed to cool to 95°C, while stirring, after which it is kept for 20 minutes without stirring, and for 10 minutes under stirring. The solution is then filtered, and acetone is added to an aliquot of the filtrate to cause the polymer dissolved therein to precipitate. The polymer thus obtained is recovered, washed, dried, and weighed to determine the weight of xylene soluble fraction.

Note 2

The analysis were carried out with an instrument Bruker AC200 at 50323 Mhz, using  $C_2D_2Cl_4$  as solvent at temperature of 120°C.

Note 3

Said test is carried out on plaques produced by an injection-moulding process in an automated injection press. The operative conditions are: melt temperature is 220°C, mould temperature is 40°C and backpressure is 10 bar.

The dimensions of the plaques are 175x74x3 mm.

The gloss is measured on the smooth side of the plaques immediately after moulding and then after 30 days' ageing in an oven at 70°C. The gloss is determined as below described. One measures the light reflected by the surface of the plaque under test. The light ray has a fixed angle of incidence. The

following simplified equation of Fresnel, which is suitable for non-metals, is used:

$$F = 1/2 [\sin^2(i-r)/\sin^2(i+r) + \tan^2(i-r)/\tan^2(i+r)] = I/I_0$$

wherein F = fraction of the measured light rays; I = emerging rays; I<sub>0</sub> = incidental rays; i = angle of incidence; r = angle of refraction;  $\sin r = (\sin i)/n$ , wherein n = refractive index. The used instrument is a photometer Zhentner 2GM 1020 suitable for angles of 45°/60°.

The gloss is given as average value.

#### Note 4

Injected-moulding plaques prepared as in note 3 and having the same dimensions are used. The stickiness is measured after 6 months' ageing at room temperature. The different stickiness of the plaques is determined by a tactile test of the operator. The scale of stickiness is explained in Table 1.

#### Note 5

One determines the variation in the time of the gloss of an injection moulded plaque, prepared as described in note 3. The plaque has dimensions of 175x74x3 mm. The gloss is immediately after preparing the plaque and after 30 days' ageing in an oven at 70°C.

#### Note 6

Said test was carried out on moulded plaques prepared as in note 3. The dimensions of the plaques were 150X250X3.2 mm. According to the above-mentioned method ASTM D-1894, version C, to determine the coefficient of friction (COF) one makes to slip a metallic slide on the smooth part of the moulded plaque. The metallic slide is prepared according to method DIN 4768. The COF has been determined both on plaques moulded at low temperature of the melt (220°C) and on plaques moulded at high

temperature of the melt (260°C) both before and after ageing in an oven at 100°C for 3 days.

Note 7

One determines the mean "peak-to-valley height" of 5 consecutive individual measuring lengths of the filtered roughness profile of the embossed plaque.

Note 8

One measures the deformation of a plaque produced by injection moulding both before ageing and after ageing in an oven at 100°C for 3 days.

Components used in the examples and comparative example

- Heterophasic composition (I) having MFR of 0.6-1 g/10 min consists of (percent by weight):
  - (A) 33% of a crystalline random copolymer of propylene and 4.3% of ethylene; the copolymer contains about 9% of a soluble fraction in xylene at 25°C and has an intrinsic viscosity [  $\eta$  ] of 1.5 dl/g;
  - (B) 6% of an essentially linear ethylene/propylene copolymer wholly insoluble in xylene at 25°C; and
  - (C) 61% of an ethylene/propylene amorphous copolymer, containing 30% of ethylene; the copolymer is wholly soluble in xylene at 25°C and has an intrinsic viscosity [  $\eta$  ] of 3.2 dl/g.

The composition was obtained by sequential polymerization in the presence of a high yield and highly stereospecific Ziegler-Natta catalyst, supported on  $MgCl_2$ .

- copolymer containing 66 wt% of ethylene and 34% by weight of 1-octene (NMR analysis), having a hardness of 75 Shore A points and a density of 0.87 g/ml. It is marketed by Dow Chemical with the trademark Engage 8200;

- copolymer containing 75 wt% of ethylene and 25% by weight of 1-octene (IR analysis according to Dow Chemical), having a hardness of 75 Shore A points and density of 0.868 g/ml. It is marketed by Dow Chemical with the trademark Engage 8150;
- copolymer containing 77.9 wt% of ethylene and 22.1 wt% of 1-butene (NMR analysis) a hardness of 85 Shore A points and a density of 0.88 g/ml. It is commercialised by Exxon Chemical with the trademark Exact 4033;
- ethylene-methyl acrylate copolymers containing 20 wt% of methyl-acrylate units. It has a MFR ratio of 2 g/10 min and density of 0.942 g/ml It is marketed by Chevron Chemical Company with the trademark EMAC SP 2205;
- styrene-isoprene-styrene block copolymers (SIS) having a hardness of 34 Shore A points. It is marketed by Shell with the trademark Kraton D-1112;
- styrene-ethylene-butylene-styrene block copolymers (SEBS) having a hardness of 75 Shore A points. It is marketed by Shell with the trademark Kraton G-1652;
- styrene-ethylene-butylene-styrene block copolymers (SEBS) having a hardness of 65 Shore A points. It is marketed by Shell with the trademark Kraton G-1657;
- pentaerithryl-tetrakis[3(3,5-di-tert-butyl-4-hydroxyphenyl) propionate marketed by Ciba-Geigy with the trademark Irganox 1010;
- bis(2,4-di-tert-butylphenyl)phosphite marketed by Ciba-Geigy with the trademark Irgafos 168;
- Irganox B 225: 50 wt% of Irganox 1010 + 50 wt% of Irgafos 168;

- 2,2'-tiodiethyl bis 3(3,5-di-tert-butyl-4-hydroxyphenyl) propionate marketed by Ciba-Geigy with the trademark Irganox 1035;
- bis (2,2,6,6-tetramethyl-4-piperidyl)sebacate marketed by Ciba-Geigy with the trademark Tinuvin 770;
- 2,5-bis(tert-butylperoxy)-2,5-dimethylhexane marketed by Akzo Nobel with the trademark Trigonox 101;
- trans-polyoctenamer rubber having an average molecular weight of  $1.0 \cdot 10^5$ , a cis/trans double bond ratio equal to 80:20, commercialised by Hüls AG with the trademark Vestenamer 8012.

#### Example 1

1st stage: 99.4 parts by weight of heterophasic composition (I), 0.1 parts by weight of Irganox 1010, 0.1 parts by weight of Irgafos 168, 0.08 parts by weight of Trigonox 101, 0.05 parts by weight of calcium stearate and 0.25 parts by weight of Tinuvin 770 were extruded in a twin-screw Maris type extruder (L/D=33 and the diameter is 45 mm) operating at a velocity of 250 rpm and at a temperature ranging from 210°-260°C.

The composition thus obtained has MFR of 16 g/10 min.

2nd stage: 88.4 parts by weight of composition coming from 1st stage, 10 parts by weight of Engage 8200 and about 1.6 parts by weight of pigments were extruded again in the same apparatus and under the same conditions of 1st stage.

The final composition has a MFR of 15.6 g/10 min.

In Table 1 are shown the hardness, stickiness, blooming, gloss, planarity and roughness of the final composition and in Table 2 the COF.

#### Example 2

The 1st stage of example 1 is repeated with the only exception that Tinuvin 770 was absent.

The composition thus obtained has a MFR of 14.6 g/10 min.

2nd stage: 88.1 parts by weight of composition coming from 1st stage, 10 parts by weight of EMAC SP 2205, 0.25 parts by weight of Tinuvin 770 and about 1.6 parts by of pigments were extruded again in the same apparatus and the same conditions of 1st stage.

The final composition has a MFR of 13 g/10 min.

In Table 1 are shown the hardness, stickiness, blooming, gloss, planarity and roughness of the final composition and in Table 2 the COF.

#### Example 3

The 1st stage of example 2 was repeated.

The composition thus obtained has a MFR of 15 g/10 min.

The 2nd stage of example 2 was repeated with the exception that 10 parts by weight of Kraton D-1112 in the place of EMAC SP 2205 was mixed to the composition coming from 1st stage.

The final composition thus obtained has a MFR of 14.7 g/10 min.

In Table 1 are shown the hardness, stickiness, blooming, gloss and roughness of the final composition and in Table 2 the COF.

#### Example 4

The 1st stage of example 2 was repeated.

The composition thus obtained has a MFR of 10.4 g/10 min.

The 2nd stage of example 2 was repeated with the exception that 10 parts by weight of Exact 4033 in the place of EMAC SP 2205 were mixed to the composition coming from 1st stage.

The final composition thus obtained has a MFR of 8.1 g/10 min.

In Table 1 are shown the hardness, stickiness, blooming and gloss of the final composition.



Comparative Example 1c

In the same apparatus and under the same conditions of step 1° of example 1 were extruded 95.8 parts by weight of heterophasic copolymer (I), 3 parts by weight of Vestenamer 8012, 0.18 parts by weight of Trigonox 101, 0.5 parts by weight of Irganox 1035 and 0.25 parts by weight of Tinuvin 770.

The final composition thus obtained has a MFR of 14.5 g/10 min. In Table 1 are shown the hardness, stickiness, blooming, gloss, planarity and roughness of the final composition and in Table 2 the COF.

Comparative Example 2c

The composition as obtained after 1st stage of example 1 was tested. The results are shown in Tables 1 and 2.

Example 5

1st stage: 99.46 parts by weight of heterophasic composition (I) and 0.04 parts by weight of Trigonox 101 were extruded in the same apparatus and the same conditions of 1st stage of example 1.

The composition thus obtained, composition (I'), has a MFR of 8 g/10 min.

2nd stage: 50 parts by weight of the composition coming from the 1st stage, 49.9 parts by weight of Engage 8200 and 0.1 parts by weight of Irganox B 215 were extruded again in the same apparatus and under the same conditions of 1st stage.

The properties of composition (I), (I') and the final composition are shown in Table 3.

Example 6

Example 5 had been repeated with the exception that 70 parts by weight of composition (I) and 29.9 parts by weight of Engage 8200 were used in the 2nd stage.

The properties of the final composition are shown in Table 3.

Example 7

70 parts by weight of heterophasic composition (I), 29.9 parts by weight of Engage 8150 and 0.1 parts by weight of Irganox B 215 were extruded in the same apparatus and under the same conditions of 1st stage of example 1.

The properties of the final composition are shown in Table 3.

Example 8

50 parts by weight of heterophasic composition (I), 49.9 parts by weight of Engage 8150 and 0.1 parts by weight of Irganox B 215 were extruded in the same apparatus and under the same conditions of 1st stage of example 1.

The properties of the final composition are shown in Table 3.

Table 1

Examples	Hardness Shore D <sup>1)</sup>	Stickiness <sup>2)</sup>	Blooming <sup>3)</sup>	Gloss <sup>4)</sup> (%)	Gloss <sup>5)</sup> (%)	Planarity <sup>6)</sup> ( $\mu\text{m}$ )		Roughness ( $\mu\text{m}$ )	
						220°C	260°C	220°C	260°C
1	24	1-2	no	83.3	29.9	123-121	122-122	82-79	81-78
2	24.5	1-2	no	82.6	22.6	134-167	137-148	78-81	79-81
3	27	2-3	no	77	21	200-177	156-130	85-81	86-82
4	29	2	low	82	23	-	-	-	-
1c	30-32	3	yes	83	73	167-154	126-125	86-83	85-81
2c	32	3	yes	80	10	127-130	167-198	84-80	

<sup>1)</sup> points; <sup>2)</sup> 1: no sticky, 2: low sticky, 3: sticky; <sup>3)</sup> on an extruded band after 6 months at room temperature;  
<sup>4)</sup> immediately after the moulding; <sup>5)</sup> after 30 days' ageing at 70°C; <sup>6)</sup> as reference a completely planar metal plaque having a roughness of 120  $\mu\text{m}$  is used, values higher than 120  $\mu\text{m}$  mean a distortion.

Table 2

Ex and comp.	COF <sup>1)</sup> before ageing	COF <sup>1)</sup> after ageing <sup>2)</sup>	COF <sup>3)</sup> before ageing	COF <sup>3)</sup> after ageing <sup>2)</sup>
1	0.51	0.58	0.63	1.06
2	0.94	1.34	1.1	1.9
4	1.0	1.7	1.1	1.4
1c	0.47	0.88	0.45	0.72
2c	0.64	1.32	0.6	1.4

<sup>1)</sup> plaque moulding at 220°C; <sup>2)</sup> 3 days' ageing in an oven at 100°C; <sup>3)</sup> plaque moulding at 260°C.

Table 3

Examples and comp. examples	5	6	7	8	Comp (I) <sup>1)</sup>	Comp <sup>2)</sup> (I')
MFR <sup>3)</sup> (g/10 min)	7.5	6.8	0.81	0.89	0.6	8
Hardness Shore D (points)	23	27	28	26	32	32
Hardness Shore A (5'') (points)	79	83	81	79	90	90
Tensile at break (MPa)	14.5	17	8.8	7.7	22	19
Elongation at break (%)	1160	1180	650	490	800	900
Tension set 100% at 23°C (%)	26	32	30	22	40	38

<sup>1)</sup> heterophasic composition (I); <sup>2)</sup> the composition is obtained in stage 1 of example 5; <sup>3)</sup> 230°C, 2.16 kg.

## CLAIMS

1. An elastomeric thermoplastic polyolefin composition comprising (percent by weight):
  - (I) 40-97% of a heterophasic olefin polymer composition comprising:
    - (A) 5-50% of a crystalline propylene homopolymer with isotactic index greater than 80% or crystalline copolymer of propylene and ethylene or a  $\text{CH}_2=\text{CHR}$   $\alpha$ -olefin, wherein R is a  $\text{C}_2\text{-C}_8$  alkyl radical, or crystalline copolymer of propylene, ethylene and a  $\text{CH}_2=\text{CHR}$   $\alpha$ -olefin, wherein R is a  $\text{C}_2\text{-C}_8$  alkyl radical, or blend thereof; said copolymers containing more than 85% of propylene and having an isotactic index greater than 80%;
    - (B) 0-20% of a crystalline copolymer fraction of ethylene with propylene or with a  $\text{CH}_2=\text{CHR}$   $\alpha$ -olefin, wherein R is a  $\text{C}_2\text{-C}_8$  alkyl radical, or both propylene and said alpha-olefin, said fraction being insoluble in xylene at ambient temperature; and
    - (C) 40-95% of an elastomeric copolymer fraction of ethylene with propylene or with a  $\text{CH}_2=\text{CHR}$   $\alpha$ -olefin, wherein R is a  $\text{C}_2\text{-C}_8$  alkyl radical, or both propylene and said alpha-olefin, and optionally with minor amounts of a diene, said copolymer fraction containing ethylene in an amount smaller than 40% and being soluble in xylene at ambient temperature;
  - (II) 3-60% of an elastomeric polymer having a hardness (Shore A, ASTM D-2240) equal to or less than 90 points selected from the group consisting of:

- 1 copolymers of ethylene with a  $C_3$ - $C_{10}$   $\alpha$ -olefin containing at least 20 wt%, preferably from 20 to 70 wt%, of  $C_3$ - $C_{10}$   $\alpha$ -olefin ( $^{13}C$ -NMR analysis) and having a  $\bar{M}_w/\bar{M}_n$  ratio less than 4;
  - 2 ethylene-methyl acrylate copolymers containing from 15 to 30 wt% of methyl acrylate units and having MFR from 1 to 10 g/10 min (ASTM D-1238);
  - 3 saturated or unsaturated styrene block copolymers, linear or branched, containing at least one comonomer selected from butadiene, butylene, ethylene and isoprene; and
  - 4 unsaturated norbornene polymers having a molecular weight over 3,000,000.
2. The composition of claim 1 wherein elastomeric copolymer (II) is selected from the group consisting of elastomeric copolymers of:
- (a) elastomeric copolymers of ethylene with 1-octene having from 20 wt% to 40 wt% of 1-octene ( $^{13}C$ -NMR analysis); preferably having density of less than 0.89 g/ml;
  - (b) elastomeric thermoplastic copolymers of ethylene with 1-butene having from 20 wt% to 40 wt% of 1-butene ( $^{13}C$ -NMR analysis); preferably having density of less than 0.89 g/ml;
  - (c) ethylene-methyl acrylate copolymers containing about 20-25 wt% of methyl acrylate units and having MFR from 1.5 to 6 g/10 min.
  - (d) unsaturated linear block copolymers of styrene with isoprene or butadiene and saturated linear block copolymers of styrene with ethylene and butylene.

3. The composition of claims 1 and 2 wherein heterophasic olefin polymer composition (I) comprises from 10 to 40 wt% of component (A), from 0 to 15 wt% of component (B) and from 50 to 75 wt% of component (C).
4. The composition of claims 1-3 wherein elastomeric copolymer (II) is a copolymer containing 66 wt% of ethylene and 34 wt% of 1-octene (<sup>13</sup>C-NMR analysis), having a hardness of 75 Shore A points (according to ASTM D-2240), MFR of 10 g/10 min (according to ASTM D 1238, condition L) and a density of 0.87 g/ml according to method ASTM D 792.
5. Use of the composition of claims 1-4 for preparing articles by injection, co-injection moulding and sequential injection moulding processes.
6. Use of the composition of claims 1-4 for preparing articles by extrusion processes.
7. Use of the composition of claims 1-4 for preparing articles by blow moulding processes.
8. Shaped manufactured articles made of the composition as claimed in claims 1-4.
9. Films and laminates made of the composition as claimed in claims 1-4.



# INTERNATIONAL SEARCH REPORT

Int'l. Application No.  
PCT/EP 98/00859

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 C08L53/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 42 11 413 A (BENECKE AG J H) 7 October 1993 see page 2, line 26 - line 33 see page 3, line 3 - line 24	1-3,5-9
X	EP 0 457 082 A (ALKOR GMBH) 21 November 1991 see page 2, line 34 - page 3, line 28	1-3,5-9
A	EP 0 611 801 A (HIMONT INC) 24 August 1994 see page 2, line 21 - line 47 see page 3, line 18 - line 24	4

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"S" document member of the same patent family

Date of the actual completion of the international search

11 June 1998

Date of mailing of the international search report

03/07/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 spo nl,  
Fax: (+31-70) 340-3018

Authorized officer

Schmidt, H

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/00859

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 4211413 A	07-10-1993	CA 2110502 A	14-10-1993
		DE 59303844 D	24-10-1996
		WO 9320146 A	14-10-1993
		EP 0587871 A	23-03-1994
		ES 2092297 T	16-11-1996
		MX 9301912 A	31-08-1994
EP 0457082 A	21-11-1991	DE 4015748 A	21-11-1991
		AT 160161 T	15-11-1997
		DE 59108889 D	18-12-1997
EP 0611801 A	24-08-1994	US 5331047 A	19-07-1994
		AT 156169 T	15-08-1997
		AU 667764 B	04-04-1996
		AU 5520694 A	25-08-1994
		CA 2115534 A	18-08-1994
		CN 1097432 A	18-01-1995
		DE 69404495 D	04-09-1997
		DE 69404495 T	29-01-1998
		FI 940752 A	18-08-1994
		JP 7026084 A	27-01-1995
		MX 9401189 A	31-08-1994
		NO 940552 A	18-08-1994
		US 5453318 A	26-09-1995